

## Antique Collection

Full grain aniline cowhide

Chrome tanning

Through dyed

Finished with oils, natural waxes and resins

Firm waxy feel

Shiny appearance and two tone effect

Average hide size				4.8 - 5.0 sq mtr
Thickness	ISO 2589			0.9 - 1.1 mm
Colour fastness to artificial light Xenon arc	UNI EN ISO 105 B02		≥ 2	Blue Scale
Colour fastness to and fro rubbing	UNI EN ISO 11640	Dry	≥ 4	Grey Scale
		Wet	≥ 4	Grey Scale
		Sweat	≥ 4	Grey Scale
Flexing Endurance	ISO 5402			50,000 Cycles
Tear Strength - Single Edge Tear	ISO 3377 - 1		> = 20	N
Determination of ph	ISO 4045		> = 3.5	pH
Difference figure (pH <4)			< = 0.7	