

**Character Collection**

Natural half-grain aniline cowhide

Chrome tanning

Through dyed

Water based system

Treated with resins aniline and waxes

Uneven slippery feel

Semi-gloss appearance

Average hide size			4.8 - 5.0	sq mtr
Thickness	ISO 2589		0.8 - 1.0	mm
Colour fastness to artificial light Xenon arc	UNI EN ISO 105 B02		≥ = 2/3	Blue Scale
Colour fastness to and fro rubbing	UNI EN ISO 11640	Dry	≥ 3	Grey Scale
		Wet	≥ 3	Grey Scale
		Sweat	≥ 2	Grey Scale
Flexing Endurance	ISO 5402		50,000	Cycles
Tear Strength - Single Edge Tear	ISO 3377 - 1		> = 20	N
Determination of ph	ISO 4045		> = 3.5	pH
Difference figure (pH <4)			< = 0.7	