

	Standard		Unit of Measurement
Thickness	ISO 2589	0.8-1.0	mm
Colour Fastness to Rubbing (Dry)	UNI EN ISO 11640; ISO 105-A02	500 / ≥ 4	Grey Scale
Colour Fastness to Rubbing (Wet)	UNI EN ISO 11640; ISO 105-A02	250 / ≥ 3/4	Grey Scale
Colour Fastness to Rubbing (Alkali Sweat Solution)	UNI EN ISO 11640; ISO 105-A02; ISO 105 E04	80 / ≥ 3/4	Grey Scale
Strength of finish adhesion	ISO 11644	≥ 2.5	N/cm
Tensile Strength	ISO 3376	≥ 100	N
Tear Resistance	ISO 3377-1	≥ 20	N
Stitch Tear Resistance	ISO 23910	≥ 50	N
Behaviour at permanent folding - 50,000 Cycles	UNI - ISO 5402	No	Visual Evaluation
Colour Fastness to light - 72 h	ISO 105 B06	Damage	Visual Evaluation
Aging	4h @ 70 Degrees Celsius	≥ 4	Grey Scale
Flammability	FMVSS 302	min 4	Visual Evaluation
ph Value	ISO 4045	< 100	mm/min
Difference figure where ph <4 or >10	ISO 4045	≥ 3, 5	
		≤ 0.7	