

<b>article</b>	<b>Mustang</b>	
<b>Width</b>	1,40 M (+/- 2%)	
<b>Length per Roll</b>	30	
<b>Composition Surface</b>	100% Polyurethane	
<b>Composition base fabric</b>	60 % Polyester + 40% Cotton	
<b>Thickness: mm</b>	1.20	
<b>Weight - grams per Linear metre</b>	740	
<b>Tear Resistance</b> (DIN 53356 Procedure A)	length lateral	>= 30N/5cm: passed with 74 >= 25N/5cm: passed with 54
<b>Tensile Strength</b> (DIN EN ISO 1412)	length lateral	>= 400 N: passed with 1202 >= 320 N: passed with 911
<b>Abrasion Resistance</b> (DIN EN ISO 105-X12)	Dry Wet	>= 5 GM-Level: passed >= 5 GM-Level: passed
<b>Light fastness (DIN EN ISSO 105-B02)</b>		>= 5 Level: passed
<b>Abrasion Resistance</b> Martindale (ISO 12947-1,2)	Dry Wet	>= 100.000 touren: passed >= 100.000 touren: passed
<b>Permanent Creasing</b> Ballyflex 23°C (DIN 53351)	length lateral	>= 100.000 touren: passed >= 100.000 touren: passed
<b>Bally Test - after Hydrolysis</b> 14d 70° 95-98% rel. LF DIN EN ISO 32100 (DIN 53351)	length lateral diagonal	>= 15.000 touren: passed >= 15.000 touren: passed >= 15.000 touren: passed
<b>Resistance to seam slippage (EN ISO 13936-2)</b>		<= 4: passed
<b>Odour</b> 23°; 40°C 24 hours VDA 270 C3 80°		1 grade: passed 3 grade: passed
<b>Inflamibility (Cigarette test)</b>		(DIN EN 1021-1): passed
<b>Clean Instructions</b>		