

<b>article</b>		<b>Nubuk Suede</b>
<b>Width</b>		1,40 M (+/- 2%)
<b>Length per Roll</b>		40
<b>Composition Surface</b>		80% Polyester + 20% cotton
<b>Composition base fabric</b>		60 % Polyester + 40% Cotton
<b>Thickness: mm</b>		.....
<b>Weight - grams per Linear metre</b>		392
<b>Tear Resistance (DIN 53356 Procedure A)</b>	<b>length lateral</b>	>= 30N/5cm: passed with 73 >= 25N/5cm: passed with 61
<b>Tensile Strength (DIN EN ISO 1412)</b>	<b>length lateral</b>	>= 400 N: passed with 764 >= 320 N: passed with 1315
<b>Abrasion Resistance (DIN EN ISO 105-X12)</b>	<b>Dry Wet</b>	>= 5 GM-Level: passed >= 5 GM-Level: passed
<b>Light fastness (DIN EN ISSO 105-B02)</b>		>= 4 and 5
<b>Abrasion Resistance (ISO 12947-1,2)</b>	<b>Dry Wet</b>	50,000 50,000
<b>Permanent Creasing Ballyflex 23°C (DIN 53351)</b>	<b>length lateral</b>	Pilling test: ISO12945-2 (Martindale): >= 4 and 5
<b>Bally Test - after Hydrolysis 14d 70° 95-98% rel. LF (DIN EN ISO 32100 (DIN 53351))</b>	<b>length lateral diagonal</b>	Color fastness to Water (<30°) staining - ISO 105 E01 >= 4
<b>Resistance to seam slippage (EN ISO 13936-2)</b>		<= 4: passed
<b>Odour 23°; 40°C 24 hours VDA 270 C3 80°</b>		Color fastness to Crocking ISO 105 X12
<b>Inflamibility (Cigarette test)</b>		DRY: 4 and 5 / WET: 4
<b>Clean Instructions</b>		