

article	Corium	
Width	1,40 M (+/- 2%)	
Length per Roll	30	
Composition Surface	100% Polyurethane	
Composition base fabric	50%Polyester+30%Cotton+10%regenerated leather	
Thickness: mm	1.40	
Weight - grams per Linear metre	890	
Tear Resistance (DIN 53356 Procedure A)	length	>= 30N/5cm: passed with 75
	lateral	>= 25N/5cm: passed with 56
Tensile Strength (DIN EN ISO 1412)	length	>= 400 N: passed with 1205
	lateral	>= 320 N: passed with 917
Abrasion Resistance (DIN EN ISO 105-X12)	Dry	>= 5 GM-Level: passed
	Wet	>= 5 GM-Level: passed
Light fastness (DIN EN ISSO 105-B02)	>= 5 GM-Level: passed	
Abrasion Resistance Martindale (ISO 12947-1,2)	Dry	>= 100.000 touren: passed
	Wet	>= 100.000 touren: passed
Permanent Creasing Ballyflex 23°C (DIN 53351)	length	>= 100.000 touren: passed
	lateral	>= 100.000 touren: passed
Bally Test - after Hydrolysis 14d 70° 95-98% rel. LF	length	>= 15.000 touren: passed
	lateral	>= 15.000 touren: passed
	diagonal	>= 15.000 touren: passed
Resistance to seam slippage (EN ISO 13936-2)	<= 4: passed	
Odour	23°; 40°C 24 hours	1 grade: passed
	VDA 270 C3 80°	3 grade: passed
Inflamibility (Cigarette test)	(DIN EN 1021-1): passed	
Clean Instructions		