

article	Uruguay
Width	1,40 M (+/- 2%)
Length per Roll	30 m
Composition Surface	100% Polyurethane
Composition base fabric	60 % Polyester + 40% Cotton
Thickness: mm	1.00
Weight - grams per Linear metre	610
Tear Resistance (DIN 53356 Procedure A)	length >= 30N/5cm: passed with 67 lateral >= 25N/5cm: passed with 42
Tensile Strength (DIN EN ISO 1412)	length >= 400 N: passed with 990 lateral >= 320 N: passed with 415
Abrasion Resistance (DIN EN ISO 105-X12)	Dry >= 5 GM-Level: passed Wet >= 5 GM-Level: passed
Light fastness (DIN EN ISSO 105-B02)	>= 5 Level: passed
Abrasion Resistance Martindale (ISO 12947-1,2)	Dry >= 100.000 touren: passed Wet >= 100.000 touren: passed
Permanent Creasing Ballyflex 23°C (DIN 53351)	length >= 30.000 touren: passed lateral >= 30.000 touren: passed
Bally Test - after Hydrolysis 14d 70° 95-98% rel. LF (DIN EN ISO 32100 (DIN 53351))	length >= 15.000 touren: passed lateral >= 15.000 touren: passed diagonal >= 15.000 touren: passed
Resistance to seam slippage (EN ISO 13936-2)	<= 4: passed
Odour 23°; 40°C 24 hours VDA 270 C3 80°	1 grade: passed 3 grade: passed
Inflamibility (Cigarette test)	(DIN EN 1021-1): passed
Clean Instructions	cotton cloth to wipe the material clean.